

Report No.: 326038412a 001 Page 1 of 6

Client: EASCO ELECTRICAL (JIANG SU) CO,LTD.

Contact Information: No.88 Chaoyang Road, Huiping Town, Qidong City, Jiangsu, P.R. China

**Identification/
Model No(s):** Halogen-free Wiring Duct
UHF-L series, UHF-S series, SDRHF series

Sample obtaining method: Sending by customer

Condition at delivery: Test item complete and undamaged.

Sample Receiving date: 2024-07-10

Testing Period: 2024-07-10 to 2024-07-18

Place of testing: Chemical Laboratory Shanghai

Test Specification:

Test result:

Customer's requirement:

1. According to RoHS (recast): Restriction of the Use of Certain Hazardous Substances in Electrical and Electronic Equipment, 2011/65/EU Annex II and its amendment

PASS

For and on behalf of
TÜV Rheinland (Shanghai) Co., Ltd.



2024-07-26

Mia Shen / Project Engineer

Date

Name/Position

Sample information is provided by customer. Test result is drawn according to the kind and extent of tests performed.
This test report relates to the above mentioned test sample. Without permission of the test center this test report is not permitted to be duplicated in extracts. This test report does not entitle to carry any safety mark on this or similar products.
"Decision Rule" document announced in our website (<https://www.tuv.com/landingpage/en/qm-gcn/>) describes the statement of conformity and its rule of enforcement for test results are applicable throughout this test report.

Test Report No.: 326038412a 001

Page 2 of 6

Material List:

Item: Halogen-free Wiring Duct
UHF-L series, UHF-S series, SDRHF series

Material No.	Material	Color	Location
A001	PC/ABS	gray	refer to photo

Test Report No.: 326038412a 001 Page 3 of 6

1. Cadmium, Lead, Chromium (VI), Mercury, Polybrominated biphenyls (PBB) and Polybrominated diphenyl ethers (PBDE)

Test Method: Total Cadmium, Lead, Mercury, Chromium
- Ref. to IEC 62321-4:2013+AMD1:2017 and IEC 62321-5:2013

Chromium (VI)
- For Metal material - Ref. to IEC 62321-7-1:2015
- For Polymer, Electronic material or others materials – Ref. to IEC 62321-7-2:2017

PBBs, PBDEs – Ref. to IEC 62321-6:2015

Test Result:

	Cd	Cr(VI)	Pb	Hg	PBBs	PBDEs
Maximum Permissible Limit (%)	0.01	0.1	0.1	0.1	0.1	0.1

Material No.	(%)					
	Cd	Cr[^]	Pb	Hg	PBBs	PBDEs
	RL (%)					
	0.001	0.001	0.001	0.001	0.01	0.01
A001	< RL	< RL	< RL	< RL	< RL	< RL

Material No.	Chromium VI content for other materials (%) RL: 0.01%
A001	<RL

- Abbreviation:**
- Pb = Lead
 - Cd = Cadmium
 - Hg = Mercury
 - Cr = Chromium
 - Cr (VI) = Chromium (VI)
 - PBBs = Total Polybrominated Biphenyls
 - PBDEs = Total Polybrominated Diphenyl Ethers
 - < = Less than
 - RL = Reporting Limit
 - n.a. = Not Applicable
 - [^] = The total Chromium have been determined
 - % = Percentage

Test Report No.: 326038412a 001

Page 4 of 6

Remark:

(*1) The Chromium (VI) content of metal sample in surface layer have been confirmed with reference to IEC 62321-7-1:2015 Annex.

	Chromium (VI) concentration	Qualitative result
Negative	<0.1µg/cm ²	The sample is negative (-ve) for Cr(VI). The Cr(VI) concentration is below the limit of quantification. The coating is considered a non-Cr(VI) based coating
Inconclusive	≥0.1µg/cm ² and ≤0.13 µg/cm ²	The result is considered to be inconclusive. Unavoidable coating variations may influence the determination. Recommendation: if additional samples are available, perform a total of 3 trials to increase sampling surface area. Use the averaged result of the 3 trails for the final determination.
Positive	>0.13 µg/cm ²	The sample is positive (+ve) for Cr(VI). Concentration is above the limit of quantification and the statistical margin of error. The sample coating is considered to contain Cr(VI).

* The reporting limit for each individual PBBs and individual PBDEs are :

Reporting Limit (%)		
PBBs	Bromobiphenyl	0.0005
	Dibromobiphenyl	0.0005
	Tribromobiphenyl	0.0005
	Tetrabromobiphenyl	0.0005
	Pentabromobiphenyl	0.0005
	Hexabromobiphenyl	0.0005
	Heptabromobiphenyl	0.0005
	Octabromobiphenyl	0.0005
	Nonabromobiphenyl	0.0005
	Decabromobiphenyl	0.0005
PBDEs	Bromodiphenylether	0.0005
	Dibromodiphenyl ether	0.0005
	Tribromodiphenyl ether	0.0005
	Tetrabromodiphenyl ether	0.0005
	Pentabromodiphenyl ether	0.0005
	Hexabromodiphenyl ether	0.0005
	Heptabromodiphenyl ether	0.0005
	Octabromodiphenyl ether	0.0005
	Nonabromodiphenyl ether	0.0005
	Decabromodiphenyl ether	0.0005

Test Report No.: 326038412a 001

Page 5 of 6

BBP, DBP, DEHP, DIBP content

Test Method: ref. to IEC 62321-8:2017

Test Result:

	BBP	DBP	DEHP	DIBP
Maximum permissible Limit (%)	0.1	0.1	0.1	0.1

Test No.	Material No.	RL (%)			
		BBP	DBP	DEHP	DIBP
		0.005			
T001	A001	< RL	< RL	< RL	< RL

Abbreviation: BBP= Benzylbutyl phthalate
 DBP= Dibutyl phthalate
 DEHP= Bis(2-ethylhexyl) phthalate
 DIBP= Diisobutyl phthalate
 < = less than
 RL = Reporting Limit
 %= percentage


Remark:

- * The maximum permissible limit is required from the amendment (EU) 2015/863 of RoHS Directive 2011/65/EU.

Test Report No.: 326038412a 001

Page 6 of 6

Sample Photo



- END -

